

Energy Solutions Casting Resins

Product Overview

Voltacast



Energy Solutions - Casting Resins

Voltacast Product Overview

Product Name	Characteristics	Typical Applications	Colour	Curing Agent	Mixing Ratio
Parts by weight					
PUR-Casting Resins, pigmented, non abrasive filled					
Voltacast 3100	Flexible	Transformers, electronics	grey	Voltacast H131	100:30
Voltacast 3100	Flexible	Transformers, electronics	grey	Voltacast H132	100:30
Voltacast 3110	Flexible, flame retardant, halogen free	Transformers, electronics	grey	Voltacast H131	100:30
Voltacast 3110	Flexible, flame retardant, halogen free	Transformers, electronics	grey	Voltacast H132	100:30
Voltacast 3200	Tough-hard, low processing viscosity	Transformers, motors (stators)	white/black	Voltacast H132	100:30
Voltacast 3210	Tough-hard, flame retardant, halogen free	Transformers, motors (stators)	white	Voltacast H132	100:20
Voltacast 3220	Tough-hard	Transformers, motors (stators)	white/black	Voltacast H132	100:20
EP-Casting Resins, pigmented, non-abrasive filled, flame retardant, halogen free, ATF-oil resistant¹					
Voltacast 3310	Tough-elastic, high thermal conductivity	Automotive, transformers, electronics, motors (stators)	black	Voltacast H134	100:14
Voltacast 3311	Elevated heat distortion temperature, high thermal conductivity	Automotive, transformers, small motors (stators), traction	blue	Voltacast H135	100:7.5
Voltacast 3311	Tough-hard, high thermal conductivity	Automotive, transformers, large motors (stators), traction	blue	Voltacast H136	100:12.5
Auxiliary Products					
Voltatex® T060	Cleaning agent for not completely cured casting resin contaminations, no hazard labeling				
Voltatex® A334	Accelerator for PUR-casting resins				

Viscosity DIN 53019	Pot Life	Thermal Conductivity	Volume Shrinkage	Shore Hardness DIN 53305	Curing Conditions	Approvals	Temperature Index IEC 60216
25°C [mPas]	room temp. [min]	ISO 22007-2 W/mK]	Curing at room temp. [%]	Curing: 5h at 80°C			
650-1350	30-50	approx. 0.35	approx. 4.8	5-15 Shore D	24h at RT ²	-	120-130
550-750	30-60	approx. 0.35	approx. 4.8	5-11 Shore D	24h at RT ²	-	120-130
700-1400	25-55	approx. 0.4	approx. 4.8	5-25 Shore D	24h at RT ²	UL 94 V2 (E72640)	120-130
450-550	35-65	approx. 0.4	approx. 4.8	45-55 Shore D	24h at RT ²	UL 94 V2 (E72640)	120-130
300-600	70-110	approx. 0.4	approx. 4.7	70-90 Shore D	24h at RT ²	-	130-140
750-1350	65-95	approx. 0.7	approx. 3.0	65-95 Shore D	24h at RT ²	UL 94 V0 (E72640)	130-140
600-1200	35-45	approx. 0.53	approx. 3.0	270-90 Shore D	24h at RT ²	-	130-140
2100-2700	> 180	approx. 1.6	< 1	60-70 Shore D	4-6h at 60°C ³	UL 94 V0 ⁴	> 155
2000-2600	70-110	approx. 1.25	< 1	80-86 Shore D	24h at RT ³	UL 94 V0 ⁴	> 155
1800-2400	70-110	approx. 1.2	< 1	73-83 Shore D	24h at RT ³	UL 94 V0 ⁴	> 155



¹ We recommend individual resistance testing with the ATF-oil to be used in every case.

² or 5h at 80°C

³ or 2-3h at 80°C

⁴ Final UL recognition pending.

Axalta Coating Systems Germany GmbH & Co. KG
Energy Solutions
Technical Service
Christbusch 25
D-42285 Wuppertal

www.electricalinsulation.com
electricalinsulation@axalta.com



The Axalta logo, Axalta™, Axalta Coating Systems™ and all products denoted with™ or® are trademarks or registered trademarks of Axalta Coating Systems, LLC and its affiliates. Axalta Trademarks may not be used in connection with any product or service that is not an Axalta product or service. Axalta Coating Systems 50 Applied Bank Blvd, Suite 300 Glen Mills, PA 19342 | 03/2024